



DESCRIPTION

DERCOLYTE® S 125 is produced from the polymerisation of beta pinene. Is a tackifying resin recommended to improve the adhesive properties (tack, adhesion, heat resistance) of solvent based adhesive formulations, particularly in pressure sensitive adhesives (PSA).

USES:

- Solvent based PSA formulated with natural or synthetic rubbers or acrylic. - Tires

TYPICAL VALUE

SPECIFICATION	UNIT	TYPICAL VALUE
Softening point, Ring and Ball	°C	125
Gardner colour, 50 resin / 50 toluene	CG	2

OTHER TECHNICAL DATA

	UNIT	TYPICAL VALUE
Molecular weight (Mw),	g/mole	2500

Soluble in aromatic, aliphatic solvents Insoluble in alcohol and ketones.

IDENTIFIERS

EINECS	Polymer. All monomers are listed	
CAS	68240-09-5	

TRANSPORT

HANDLING AND STORAGE	Under cover and at temperature below 30°C
STABILITY	About 18 months - storage conditions and inventory control must be observed.
Packaging	Pellets in 25 kg net weight paper bags on wrapped pallets 1000 kg net weight. Pellets in 1000 kg net weight Big Bags.
CUSTOMS TARIFF	3911100090

The data herein are based on our knowledge about above product. They are without conditions or warranties, expressed or implied regarding the uses of the product. DRT analytical methods are available on request.

TECHNICAL DATA SHEET / 08.03.2023



www.drt.fr

