

KRONOS 1071

Titanium Dioxide

for fibers and inks

Applications

- Acrylic, rayon and acetate fibers
- UV-cured printing inks
- Leather finishes
- Masterbatches for polyester fibers

Properties

KRONOS 1071 Titanium Dioxide

- displays excellent delustering efficiency and a neutral tone in fibers
- disperses readily
- shows minimum abrasion
- exhibits higher lightfastness than untreated anatase pigments
- provides good optical properties in coatings in combination with optical brighteners

Product Characteristics

Production	anatase pigmen	it produced by the sulfate process
Surface treatment		aluminium and silicon compounds
TiO ₂ content (DIN EN ISO 591)		≥ 96%
Standard classification (DIN EN ISO 591-1)		591-1) A 2
ASTM D 476		Туре І
Density (DIN EN ISO 787-10)*		3.8 g/cm ³
Bulking value*		0.26 l/kg (0.03 gal/lb)
Oil absorption (DIN	EN ISO 787-5)*	22 g/100 g pigment
Color index		Pigment White 6 (77891)
CAS No.		13463-67-7
REACH Registration	No.	01-2119489379-17-xxxx

^{*} Typical value

The information contained herein only applies to the specified KRONOS product, and, while not guaranteed, is, to the best of our knowledge, true and accurate as of the date of publication of this information. KRONOS assumes no obligation or liability in connection with the use of any information in this document, and NO WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE, OR WARRANTY OR GUARANTY OF ANY OTHER KIND, EXPRESS OR IMPLIED, IS MADE BY VIRTUE OF THIS DOCUMENT REGARDING PERFORMANCE, SAFETY, SUITABILITY, STABILITY OR OTHERWISE. It is the responsibility of the user to determine the suitability of the product for its own particular purpose, and the user assumes all risks of use and handling of the product. This document does not create any contractual rights between KRONOS and the user. © 2022 KRONOS Worldwide, Inc. KRONOS® and logo designs associated therewith are trademarks of Kronos Worldwide, Inc. and/or its subsidiaries or affiliates.

© KRONOS INTERNATIONAL, Inc., 2022