

Product information

Dynasylan® AMEO

3-Aminopropyltriethoxysilane

Technical data

Properties and test methods	Value	Unit	Method
Refractive index n (20,D)	арргох. 1.422	-	DIN 51423
Boiling point (4 hPa)	арргох. > 68	°C	DIN 51356
Flash point	арргох. 93/ 199	°C/°F	DIN 51758
Viscosity (20 °C/ 68 °F)	approx. 1.85/ 1.95	mPa·s / cSt	DIN 53015
Density (20 °C/ 68 ° F)	арргох. 0.95	g/cm ³	DIN 51757

Registrations

Dynasylan® AMEO

EINECS/ELINCS (EU):	Yes
AICS (Australia):	Yes
DSL/NDSL (Canada):	Yes
PICCS (Philippines):	Yes
TSCA (USA):	Yes
IECSC (P.R. China):	Yes
ENCS (Japan):	Yes
ECL (South Korea):	Yes

Dynasylan* AMEO is a bifunctional silane possessing a reactive primary amino group and hydrolyzable ethoxysilyl groups.

The dual nature of its reactivity allows **Dynasylan®** AMEO to bind chemically to both inorganic materials (e.g. glass, metals, fillers) and organic polymers (e.g. thermosets, thermoplastics, elastomers) thus functioning as an adhesion promoter, crosslinker, and/or surface modifier.

Dynasylan® AMEO is a colorless to slightly yellowish low-viscosity liquid with an amine-like odor. It is soluble in alcohols, and aliphatic or aromatic hydrocarbons.

In addition **Dynasylan**[®] AMEO is completely and immediately soluble in water (with reaction).

Safety and handling

Before considering the use of Dynasylan® and Protectosil® products please read its Material Safety Data sheet (MSDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use. The Material Safety Data Sheet is available after registration on our website www.dynasylan.com or upon request from your local representative, customer service or from Evonik Industries AG, Product Safety Department, E-MAIL sds-im@evonik.com.

Packaging and storage

Dynasylan° AMEO is supplied in 25 kg,180 kg drums and 900 kg containers. In the unopened container **Dynasylan**° AMEO has a shelf life of one year.

Properties and application

Dynasylan* AMEO is an important additive for many applications.

Examples are:

- glass fiber/glass fabric composites: as a finish or size constituent
- mineral fiber insulating materials and abrasives: as an additive to phenolic resin binders
- foundry resins: as an additive to phenolic, furan and melamine resins
- sealants and adhesives: as a primer or additive and for chemical modification
- mineral-filled polymers (composites) or HFFR cables: for pretreatment of fillers and pigments
- paints and coatings: as an additive and primer for improving adhesion to the substrate.
- as a primer for glass and metal

The most important effects which can be achieved through the use of **Dynasylan*** AMEO are:

improved product properties, such as

- improved mechanical properties, for example flexural strength, tensile strength, impact strength and modulus of elasticity
- improved moisture and corrosion resistance
- improved electrical properties, for example dielectric constant, volume resistivity

improved processing properties, such as

- adhesion
- better filler dispersion
- rheological behavior: reduction in viscosity, Newtonian behaviour
- higher fillerloading

Reactivity

In the presence of water, the ethoxy groups of **Dynasylan*** AMEO hydrolyze and form reactive silanol (Si-OH) groups which can bond to a variety of inorganic substrates. Upon hydrolysis ethanol is released. The organophilic amino group of **Dynasylan*** AMEO can react with a suitable polymer.

The hydrolysis of **Dynasylan**® AMEO takes place autocatalytically. Hydrolyzates could be stable for concentrations higher than 10% for > 1 year. The pH of the aqueous solution is about 11.

Examples of suitable inorganic substrates are glass, glass fibers, glass wool, mineral wool, silicic acid, quartz, cristobalite, wollastonite, mica as well as aluminum trihydrate, magnesium dihydrate, kaolin, talc, other silicate fillers, metal oxides and metals.

Dynasylan* AMEO may be used with such polymers as epoxy, phenolic, furan and melamine resins, polyurethanes, PA, PBT, PC, EVA, modified PP, PVB, PVAC, PVC, PS, nitril Kautschuk, polyester, acrylates and silicones.

Dynasylan® AMEO can undergo reactions with ketone or ester solvents. Silane or silanized substrates can react with carbon dioxide to form the corresponding carbonates and/or carbamates. Product modifications are possible through addition reactions with suitable monomeric or polymeric compounds (e.g. isocyanates, epoxides, etc.).

Processing

Dynasylan* AMEO may be used as a constituent of aqueous sizes neat, or added to the polymer as an additive. In higher concentrations chemical modification can be achieved by reaction with suitable functional monomers or polymers, for example those containing epoxy groups.

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. EVONIK DISCLAIMS ALL REPRESENTATIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, AND SHALL HAVE NO LIABILITY FOR, MERCHANTABILITY OF THE PRODUCT OR ITS FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE), OR OTHERWISE. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

Europe/Middle-East/Africa/RoW Evonik Industries AG

Inorganic Materials Rodenbacher Chaussee 4 63457 Hanau-Wolfgang Germany PHONE +49 6181 59 13636 FAX +49 6181 59 13737 dynasylan@evonik.com www.dynasylan.com

Asia / Pacific Evonik Degussa (SEA) Pte. Ltd.

Inorganic Materials 3 Internatioanl Business Park #07-18, Nordic European Centre Singapore 609927 PHONE +65 6809 6830 FAX +65 6809 6630 dynasylan@evonik.com www.dynasylan.com

Asia / Pacific Evonik Taiwan Ltd.

Inorganic Materials Artist Construction Bldg. 9F, No. 133 Min Sheng East Road, Sec 3 Taipei, 105 Taiwan, R.O.C. Taiwan PHONE +886 227 17 1242 FAX +886 227 17 2106 dynasylan@evonik.com www.dynasylan.com

North America Evonik Degussa Corporation

Inorganic Materials
P.O. Box 677
299 Jefferson Road
Parsippany, NJ 07054-0677
USA
PHONE (TOLL FREE) +1 800 237 67 45
PHONE +1 973 929 8513
FAX +1 973 929 8503
dynasylan@evonik.com
www.dynasylan.com

Asia / Pacific Evonik Degussa (Shanghai) Co. Ltd.

Inorganic Materials 55, Chungdong Road Shanghai 201108 P.R. China PHONE +86 21 6119 1053 FAX +86 21 6119 1075 dynasylan@evonik.com www.dynasylan.com

Asia / Pacific Evonik Japan Co. Ltd

Inorganic Materials
12th Floor Monolith Building
2-3-1, Nishi-Shinjuku-ku
Tokyo 163-0912
Japan
PHONE +81 353 23 7300
FAX +81 353 23 7399
dynasylan@evonik.com
www.dynasylan.com

Latin America Evonik Brasil Ltda.

Inorganic Materials Alameda Campinas, 579 01404-000 São Paulo-SP Brazil PHONE +55 11 3146 4123 FAX +55 11 3146 4109 dynasylan@evonik.com www.dynasylan.com

Asia / Pacific Evonik Korea Ltd.

Inorganic Materials 94, Galsan 1-dong Bupyeong-gu Incheon, 403-081 Korea PHONE +82 32 510 2433 FAX +82 32 505 2510 dynasylan@evonik.com www.dynasylan.com

Asia / Pacific Evonik India Pvt. Ltd.

Inorganic Materials Krislon House Saki Vihar Road, Anderi (E) Mumbai - 400 072 India PHONE +91 226 7238 800 FAX +91 226 7238 811 dynasylan@evonik.com www.dynasylan.com

