

TECHNICAL DATA SHEET

CRAYVALLAC® WN-3025

Micronized polyethylene wax with good gloss retention

Micronised wax

TYPICAL CHARACTERISTICS

|                            |                             |
|----------------------------|-----------------------------|
| Nature                     | Polyolefin                  |
| Appearance                 | Off-white micronized powder |
| Active Content (%)         | 100                         |
| Particle size distribution | DV. 5 : 5.0                 |
| Bulk density               | 0.25-0.30                   |

DESCRIPTION

CRAYVALLAC® WN-3025 is a finely micronized hard polyethylene wax. CRAYVALLAC® WN-3025, with its well-balanced performance properties, is of particular interest to the ink formulator. Here it provides an excellent balance between high rub resistance and good slip, yet with minimal detracton from gloss.

RECOMMENDED ADDITION LEVEL

0.5 – 3.0% under low to medium shear dispersion

STANDARD PACKAGING

Other packaging may be available upon request

- 15 Kg Bag

HANDLING & STORAGE

It should be stored in the original containers in a dry place at temperatures between 5°C (41°F) and 30°C (86°F). Avoid exposure to direct sunlight or frost. In these conditions, this product should be used within 48 months from production.

PROCESSING INSTRUCTIONS

CRAYVALLAC® WN-3025 is readily dispersed into coating formulations using a variety of techniques e.g. high-speed dispersers, bead mills and triple roll mills. In general, micronised waxes are best incorporated into coating systems by premixing with the binder. Alternatively, waxes may be added to the formulation immediately following the dispersion stage but prior to the final letdown.

HEALTH AND ENVIRONMENTAL DATA

For safe handling please refer to the Safety Data Sheet. For more information about health and environmental data, please contact us.

MARKETS

- Coatings & Inks
- Architectural Coating
  - Graphic Arts
  - Industrial Coating

KEY BENEFITS

FORMULATION

- Ready to use
- Easy handling
- Post addition



FILM PROPERTIES

- Gloss
- Scratch resistance
- Abrasion resistance



SAFER SOLUTIONS

- APEO Free\*
- Heavy Metal Free\*
- Solvent Free\*

\* Not intentionally added but not specifically measured (not part of product specification)

Headquarter: Arkema France  
420, rue d'Estienne d'Orves  
92705 Colombes Cedex – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790  
arkema.com