

## Technical Data Sheet

### Bayoxide® E AB 21

#### Description

Type	Technical Oxide
Delivery form	Powder
Chemical class	Synthetic iron oxide $\gamma$ - $\text{Fe}_2\text{O}_3$
CAS-No.	1309-37-1
REACH registration no.	01-2119457614-35

#### Specified Technical Data

Technical Data	min	max	Test method
$\text{Fe}_2\text{O}_3$ Content [%] (of sample calcined at 850 °C)	97.5		No. 036 <sup>41</sup>
Content $\text{SiO}_2$ [%]		1	Atomic spectroscopy
Heavy metal content [mg/kg] (Sum of Cu, Pb, Hg, Cd)		50	Atomic spectroscopy
Specific Surface Area (BET) [ $\text{m}^2/\text{g}$ ]	22	30	ISO 9277:2003
Loss on ignition at 1000 °C, 0.5 h [%]		1.5	DIN 55913:1972
Moisture content (ex works) [%]		0.9	DIN EN ISO 787-2:2021
pH value	6.0		DIN EN ISO 787-9:1995
Predominant particle size [ $\mu\text{m}$ ]	0.4	2.0	ISO 13320:2009
Mn [mg/kg]	1000	3500	Atomic spectroscopy
Zn [mg/kg]		500	Atomic spectroscopy

<sup>41</sup> Please use our contact form on the Internet at [www.bayferrox.com](http://www.bayferrox.com) for more information.

<sup>53</sup> Minor elements may arise from the raw materials used. However, these are firmly bound to the crystal lattice as ions.

## Bayoxide® E AB 21

### Packaging

Our products are supplied in various types of packaging. To find out in which types of packaging this product is offered, please ask your local contact or use our contact form on the Internet at [www.bayferrox.com](http://www.bayferrox.com)

### Transport and Storage

General storage conditions:	Protect against weathering. Store in a dry place and avoid extreme fluctuations in temperature.
Special conditions for opened packaging:	Close bags after use to prevent the absorption of moisture and contamination.
Shelf life:	<p>This product has an excellent shelf life. We recommend that this product is used within ten years of the date of manufacture and limit our product warranty to this period. During the first ten years after the date of manufacture we are able to ensure compliance with this specification, provided the material has been stored as stated above and the packaging materials remain undamaged. It must be taken into account that the packaging mean can have a shelf life considerably shorter than the one for this product. All recommendations and warnings given on the packaging must strictly be adhered to. Deviations from storage conditions can lead to undesired changes on side of the packaging materials. These succumb to ageing which may also lead to compromising their capability. Concerning their estimated service life we differentiate between the following packaging materials:</p> <p>All kinds of bags (Paper and PE) ..... 5 years All kinds of Bulk bag ..... 3 years</p> <p>With respect to our Bulk Bags we recommend to avoid UV-radiation because the sewing material of the lifting loops is stabilized against degradation by UV-radiation for appr. 1000 h incident sun radiation for the climate of Central Europe. A more intense sun radiation can shorten this period significantly. In cases of doubt the lifting loops must be checked thoroughly.</p>

### Safety

Classification	The product is not classified as dangerous under the relevant EC Directives and corresponding national regulations valid in the individual EU member states. It is not dangerous according to transport regulations.
Additional information	<p>In countries outside the EU, compliance with the respective national legislation concerning the classification, packaging, labelling and transport of dangerous substances must be ensured.</p> <p>The safety data sheet should be observed. This contains information on handling, product safety and ecology. The safety data sheet is available at <a href="http://www.bayferrox.com">www.bayferrox.com</a>.</p>

## Bayoxide® E AB 21

### Status of Registration (not specified)

The components of this product are listed on the following inventories:				
Europe: EINECS	USA: TSCA-active	Canada: DSL	Australia: AICS	New Zealand: NZIOC
Philippines: PICCS	Japan: ENCS + ISHL	Korea: ECL	China: IECSC	Taiwan: TCSI