

TEGO® Airex 904 W

DESCRIPTION

TEGO® Airex 904 W is a very effective deaerator concentrate based on polyether siloxane technology. Very effective against micro-foam in combination. Offers good compatibility.

KEY BENEFITS

- good balance of compatibility and effectiveness
- highly suitable for medium- to low-viscosity formulations
- highly suitable for airless or airmix applications

APPLICATION RECOMMENDATION

Brush application/roller application



Airless spraying



Compressed air spraying



Flexo/gravure printing



Dip coating, flow coating, curtain coating



Flooring



SUITABILITY

waterborne	solventborne
●	●
2-pack 100%	radiation-curing
●	●
addition to the grinding stage	addition to the let-down stage
●	●

● not suitable ● partly suitable ● suitable

TYPICAL APPLICATIONS

- Plastic coatings
- Protective coatings
- General industrial coatings
- Wood coatings

TECHNICAL DATA

active matter content	100 %
appearance	turbid liquid
chemical description	polyether siloxane copolymer, contains fumed silica
solvent	solvent-free

SOLUBILITY

Water	Ethanol
●	●
TPGDA	Butylacetate
●	●
Mineral Spirits	
●	

● not soluble ● partly soluble ● soluble

RECOMMENDED ADDITION LEVEL

As supplied calculated on total formulation: 0.1 - 1.5 %

PROCESSING INSTRUCTIONS

- Haziness caused by low temperature is reversible. This does not affect the performance of the product.
- Addition to the coating as supplied or as a predilution is possible.
- Stir before use!

HANDLING & STORAGE

When stored in an original unopened packaging between -40 and +40 °C, the product has a shelf life of at least 24 months from the date of manufacture.

MSDS & REGULATORY INFORMATION



This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Resource Efficiency GmbH | Goldschmidtstraße 100, 45127 Essen, Germany | Telefon +49 201 173-2222 Telefax +49 201 173-1939 | www.coating-additives.com