

Technical Data Sheet

Revision Date: 2024-2-19

NO. PCS_0135

Name: WANNATE™ HT-800

Version: 1.0

Application

WANNATE™ HT-800 (1,6-hexamethylene diisocyanate based polyisocyanate) is a solvent free aliphatic polyisocyanate based on hexamethylene diisocyanate (HDI), colorless to slightly yellowish clear liquid.

Equivalent Weight ~ 382

Density at 25 °C ~ 1.12 g/cm³

WANNATE™ HT-800 is a kind of flexibilizing HDI trimer. It can be used as the hardener component for lightfast two-component polyurethane coatings with high resistance to chemicals and weathering, very good gloss retention and outstanding mechanical properties. Preferred co-reactants are polyacrylates or polyester polyols.

The main applications for coatings based on WANNATE™ HT-800 are automotive refinishing, transportation, industrial finishing and plastics.

Specification

| Properties | Unit | Specification |
|--------------------|-------|---------------|
| NCO Content | % | 10.50 ~ 11.50 |
| Viscosity (25 °C) | mPa·s | 4000 ~ 7000 |
| Chromatic Number | APHA | ≤ 80 |
| HDI content | % | <0.20 |

Package(s)

220 kg Metal drum

IBC

ISO TANK

Other packaging available according to customer needs

Storage / Solubility

Storage in original container. Protect from moisture, heat and foreign material.

WANNATE™ HT-800 is sensitive to moisture. Storage at higher temperatures may result in increasing of color and viscosity.

WANNATE™ HT-800 can be thinned with esters, ketones and aromatic hydrocarbons such as ethyl acetate, butyl acetate, methoxypropylacetate, acetone, methyl ethyl ketone, methyl isobutyl ketone, cyclohexanone, toluene, xylene, solvent naphtha 100 and mixtures thereof. Generally speaking, it has good compatibility with the solvents listed. However, the solutions formed must be tested for their storage stability. Only PU grade solvents should be used (max.0.05% water, absence of reactive groups such as hydroxyl or amino groups). Aliphatic hydrocarbons are unsuitable as solvents.

WANNATE™ HT-800 is not recommended to be thinned to a lower solid content. Prolonged storage of a solution with a lower content may result in turbidity or sedimentation, even gelation.

Compatibility

WANNATE™ HT-800 can be mixed with the following products: aliphatic polyisocyanates, polyester polyols, aromatic polyisocyanates and polyacrylates

Shelf Life

WANNATE™ HT-800 must be stored in tightly sealed container. It can be stored for at least 6 months at temperatures between 0 and 30 °C

**For more information about safety and environment, please refer to our MSDS
or contact our customer service center.**

Version Information:

Date of first issue: Feb. 19, 2024

For further information please contact us:

Address: Wanhua Chemical Group Co., Ltd.

 No.3, Sanya Rd, YEDA, Yantai, Shandong Province, 264006, China

Customer service: Tel: +86 (535) - 8203244 Fax: +86 (535) - 3388222-3244

Web-site: <http://www.whchem.com> E-mail: PCS@whchem.com

The information provided here is for reference only. The specification will be provided in the quality certificate or in the contract. It is the user's responsibility to test the material and its suitability for a process. We have no control over what another party does with the material and we cannot take any responsibility for another party's action. Nor will we be responsible for any indirect damages while using our products. The user is welcome to contact our customer and technical service center with questions on our products.