



D.E.H.™ 589

Epoxy Curing Agent

Description

D.E.H.™ 589 cycloaliphatic amine hardener is used as a curing agent for epoxy resins. It is used where an optimum balance between working time and cure speed is required. It results in a blush-free product and has good water spot resistance and excellent chemical resistance. It offers good low temperature cure and can also be used as an accelerator for other hardeners in coatings and civil engineering applications.

Advantages

- Good water spot resistance
- Good low temperature cure
- Low viscosity

Typical Applications

This product is suitable for use in applications such as:

- Industrial flooring
- Sealers and primers
- Tank lining

Typical Properties

Property ⁽¹⁾	Method	Value
Appearance	Visual	Clear
Color, Gardner		Max 2
Density @ 25°C (g/ml)	ASTM D4052	1.02
Viscosity @ 25°C (mPa•s)	ASTM D445	50-100
Amine value [mgKOH/g]	ISO 9702	323-379
Amine Hydrogen Equivalent Weight	Calculated	83
Shelf Life (Months)		12

(1) Typical properties, not to be construed as specifications.

Typical Handling Properties

Property	Method	Value
		D.E.R. 331™
		D.E.H. 589
Dry time (hrs)	ASTM D1640-03	5-8
Gel Time (min/100 g mass @25°C) ²		20-25
Mix ratio, phr (weight)		44

(2) Tested by Paul N. Gardner Standard Model Gel Timer

Typical Performance Properties³

Property	Method	Value
		D.E.R. 331™
		D.E.H. 589
Mix ratio, phr (weight)		44
Film appearance	Visual	Glossy
Glass Transition Temperature (°C) ⁽⁴⁾		82
Hardness Shore D	ASTM D2240	74
Cross Hatch Adhesion	ASTM D3359	
@ 25°C/50% relative humidity		2B
@ 25°C/95% relative humidity		2B
Blushing		
@ 25°C/50% relative humidity		No
@ 25°C/95% relative humidity		No
Flexural Strength (psi)		16418
Flexural Modulus (thousand psi)		515
Tensile Strength (psi)		9181
Tensile Modulus (thousand psi)		478
Elongation %		2.4

⁽³⁾ Unless otherwise specified, properties obtained after more than 7 days cure at ambient temperature

⁽⁴⁾ Glass transition temperature measured by DSC

Safety and Handling

The Dow Chemical Company provides its customers with a product specific Material Safety Data Sheet (MSDS) or Safety Data Sheet (SDS) to cover potential health effects, safe handling, storage, use and disposal information. Dow strongly encourages its customers to review the MSDS or SDS on its products and other materials prior to their use.

This curing agent should retain its chemical properties for a period of at least 12 months.

For further handling information, consult the Dow brochure entitled, *DOW Epoxy Curing Agents Product Stewardship Manual, Safe Handling and Storage*, Form No. 296-01331 and the Dow technical bulletin, *Product Coding, Shelf-life and Storage Stability*, Form No. 296-01657.

Product Stewardship

The Dow Chemical Company has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis of our Product Stewardship philosophy by which we assess the health and environmental information on our products and then take the appropriate steps to protect employee and public health and the environment. The Dow Chemical Company has enduring commitments to Responsible Care® in the management of chemicals worldwide. Our Product Stewardship program rests with every individual involved with Dow products from the initial concept and research to the manufacture, sale, distribution, and disposal of each product.

Customer Notice

Dow encourages its customers and potential users of Dow products to review their applications for such products from the standpoint of human health and environmental quality. To help ensure that Dow products are not used in ways for which they were not intended or tested, Dow personnel are available to assist customers in dealing with ecological and product safety considerations. Your Dow sales representative can arrange for the proper contacts. Dow literature, including MSDS or SDS, should be consulted prior to the use of Dow products.

Medical Application Policy

Dow will not knowingly sell or sample any product or service ("Product") into any commercial or developmental application that is intended for:

- (a) permanent (long term) contact with internal body fluids or internal body tissues. Long term is a use which exceeds 72 continuous hours;
- (b) use in cardiac prosthetic devices regardless of the length of time involved (cardiac prosthetic devices include, but are not limited to, pacemaker leads and devices, artificial hearts, heart valves, intra-aortic balloons and control systems and ventricular bypass assisted devices);
- (c) use as a critical component in medical devices that support or sustain human life; or
- (d) use specifically by pregnant women or in applications designed specifically to promote or interfere with human reproduction.

Additionally, all Products intended for use in pharmaceutical applications must pass the then current Pharmaceutical Liability Guidelines. For additional information please contact your regular Dow representative.

Food Contact Applications

This epoxy curing agent will not comply with the U.S. Food, Drugs and Cosmetics Act as amended under Food Additive Regulation 21 CFR 175.300.

Also consult the Dow data sheet, *Food Additive Status for Epoxy Resins, Curing Agents and Epoxy Novolac Resins*, Form No. 296-01425.

Regulatory Status

For more information on the regulatory status of this product, please refer to the MSDS or SDS for this product.

Chemical Inventory Listing

United States TSCA

- (1) Please refer to the MSDS or SDS for this product to ensure this CAS number is consistent with the product(s) you use.

Contact information:

North America: 800-441-4369
+1-989-832-1426
+1-989-832-1465 (fax)
Mexico: +1-800-441-4369
Brazil: +55-11-5188-9222
+55-11-5188-9749 (fax)
Europe: +800-3-694-6367
+32-3-450-2240
+32-3-450-2815 (fax)
Asia Pacific: +800-7776-7776#
+800-7779-7779# (fax)
+60-3-7958-3392
+60-3-7958-5598 (fax)

except Indonesia and Vietnam

<http://www.dowepoxy.com>

Notice: No freedom from any patent owned by Dow or others is to be inferred. Dow assumes no obligation or liability for the information in this document. The information provided herein is presented in good faith and is based on the best of Dow's knowledge, information, and belief. Since use conditions at non-Dow facilities are beyond Dow's control and government requirements may differ from one location to another and may change with time, it is solely the Buyer's responsibility to determine whether Dow's products are appropriate for the Buyer's use, and to assure the Buyer's workplace, use, and disposal practices are in compliance with applicable government requirements. Consequently, Dow assumes no obligation or liability for use of these materials and makes no warranty, express or implied. The user of the information provided is solely responsible for compliance with any applicable government requirements. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

