

Protectosil® 266 F

Silane water-repellent for masonry.

Technical Data

Properties and test methods	Value	Unit	Method
Flash point	> 25	°C	EN 22719
Active ingredient content	> 97	%	-
Density (20°C)	1.035	g/cm ³	DIN 51757
Appearance	clear, colorless to yellow liquid	-	-
Solvent	solvent-free	-	-
Viscosity	35	mPa • s	DIN 53015

Registration

Protectosil® 266 F

EINECS/ELINCS (EU):	Yes
AICS (Australia):	No
DSL/NDL (Canada):	*
PICCS (Philippines):	Yes
TSCA (USA):	Yes
IECS (P.R. China):	*
ENCS (Japan):	Yes
ECL (South Korea):	Yes
* = Information upon request	

Silane water-repellent for masonry.

Protectosil® 266 F is a free-flowing colorless to slightly yellow, frost resistant liquid based on a silane/ siloxane. Protectosil® 266 F can be applied at full-strength or after dilution with suitable solvents, such as ethanol or white spirit.

Safety and Handling

Before considering the use of Protectosil® products please read its Safety Data sheet (SDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use. The Safety Data Sheet is available on our website www.protectosil.com or upon request from your local representative, customer service or from Evonik Operations GmbH, Product Safety Department, E-MAIL sds-hu@evonik.com.

Packaging and Storage

Provided that moisture is excluded, Protectosil® 266 F has a shelf life of at least 12 months if stored in originally sealed containers. Protectosil® 266 F is supplied in 24 l PE canisters and 192 l plastic lined steel drums and 913 l bulk containers. The material should be stored at temperatures between -10° C and 40° C.

Properties and Use

For waterproofing absorbent mineral facade construction materials such as:

- plaster facades
- sand-lime brickwork
- brickwork
- autoclaved aerated concrete
- cement fiber board

The substrates to be treated should be air-dry and clean in order to ensure deep penetration of the active ingredient. During application the outside temperature and the temperature of the substrate should be within the range from 5 to 40 °C. The material should not be applied if there is a strong wind or if it is raining. The material must not come into contact with water either before or during use. Protectosil® 266 F can be applied at full-strength or after dilution with suitable solvents. We recommend a minimum application concentration of 20% by weight (which corresponds to 1 part Protectosil® 266 F and 4 parts solvent).

Product Characteristics:

- watervaporpermeable, colorless impregnation
- not film-forming
- effective on hairline cracks up to 0.3 mm
- good reduction of the water absorption
- good penetration
- suitable as a primer for facade topcoat
- frost resistant

Application

Suitable solvents are:

- Ethanol water free* (denatured with petroleum hydrocarbons)
- Aliphatic hydrocarbon solvents (pentane, hexane, heptane, etc.)
- Aromatic hydrocarbon solvents (toluene, xylene)
- White spirit

* highly recommended solvent

The amount to be applied depends to a large extent on how absorbent the substrate is. The exact amount to be applied must be determined by a trial application. Typical product consumptions are >180 g/m² for concrete, >210g/m² for sand limestone and > 240g/m² and more for brick. In order to reach these consumption rates it might be necessary to apply the material in several steps. The prepared solution of Protectosil® 266 F must be applied by flowcoating to the saturation point. This is achieved by allowing it to flow without pressure against the surface to be treated. All liquid delivery devices are suitable (airless sprayguns, for example). The material must not be atomized or applied with a brush.

Processing

The prepared solution of Protectosil® 266 F must remain in contact with the substrate for several seconds as a liquid film. Horizontal surfaces should have a shiny, wet appearance for 3-5 seconds. Vertical surfaces should exhibit a 30-50 cm shiny curtain of liquid. All equipment and containers must be clean and dry. After use they can be cleaned with any organic solvent (methyalted spirit, petrol or thinners). Non-absorbent substrates such as glass, wood, plastic and metal cannot be treated with the prepared solution of Protectosil® 266 F. In the worst case, the product not absorbed by the substrate may react with atmospheric moisture to form a greasy, glossy silicone resin film. Substrates such as mentioned above should be covered before application. If they nevertheless become contaminated, the resulting film can be easily removed if cleaned immediately using conventional cleaning agents, or alcohol (spirit of soap) in difficult cases. Glass, wood and metal are not attacked by the prepared solution of Protectosil® 266 F. Neither are most plastics used in construction. If in doubt, carry out a preliminary test. Plants in the vicinity of the substrate to be treated should be protected against contact with the solution.

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

Europe / Middle-East / Africa**Evonik Operations GmbH**

Silanes Business Line
Rodenbacher Chaussee 4
63457 Hanau-Wolfgang
Germany
FAX +49 6181 59 713 915
protectosil@evonik.com
www.protectosil.com

Asia / Pacific**Evonik (SEA) Pte. Ltd.**

Silanes Business Line
3 Internatioanl Business Park
#07-18, Nordic European Centre
Singapore 609927
PHONE +65 6809 6906
FAX +65 6809 6699
protectosil@evonik.com
www.protectosil.com

Asia / Pacific**Evonik Taiwan Ltd.**

Silanes Business Line
Artist Construction Bldg
9F, No. 133
Min Sheng East Road, Sec 3
Taipei, 105 Taiwan, R.O.C.
Taiwan 10596
PHONE +886 227 17 1242 #247
FAX +886 227 17 2106
protectosil@evonik.com
www.protectosil.com

North America**Evonik Corporation**

Silanes Business Line
299 Jefferson Road
Parsippany, NJ 07054
USA
PHONE (TOLL FREE) +1 800 828 0919
protectosil@evonik.com
www.protectosil.com

Asia / Pacific**Evonik (Shanghai) Co. Ltd.**

Silanes Business Line
55, Chungdong Road
Shanghai 201108
P.R. China
PHONE +86 21 6119 1660
FAX +86 21 6119 1075
protectosil@evonik.com
www.protectosil.com

Asia / Pacific**Evonik Japan Co. Ltd**

Silanes Business Line
12th Floor Monolith Building
2-3-1, Nishi-Shinjuku-ku
Tokyo 163-0912
Japan
PHONE +81 353 23 7446
FAX +81 353 23 7397
protectosil@evonik.com
www.protectosil.com

Region Central and South America**Evonik Brasil Ltda.**

Silanes Business Line
Rua Arquiteto Olavo Redig de Campos, 105
Torre A - 04711-904 São Paulo- SP
Brazil
PHONE +55 11 3146 9627
protectosil@evonik.com
www.protectosil.com

Asia / Pacific**Evonik Korea Ltd.**

Silanes Business Line
3F (Nongshim Sungmookwan B/D)
112 Yeouidaebang-Ro
Dongjak-Gu
Seoul, 07057
Korea
PHONE +82 2320 4778
FAX +82 2783 2520
protectosil@evonik.com
www.protectosil.com

Asia / Pacific**Evonik India Pvt. Ltd.**

Silanes Business Line
Krislon House
Saki Vihar Road, Anderi (E)
Mumbai - 400 072
India
PHONE +91 226 7238 809
FAX +91 226 7238 811
protectosil@evonik.com
www.protectosil.com