

CRYSTIC[®] VE671

Vinyl Ester Resin

Introduction

Crystic VE671 is an epoxy Bisphenol A based standard vinyl ester resin. Crystic VE671 has outstanding chemical resistance to a wide range of substances, (acids, alkalies, oxidising agents) at room and elevated temperatures.

Application

It is suitable for fabrication of fibre reinforced composites by all conventional techniques (contact moulding, filament winding and injection moulding) and for use in many chemical processing industry applications (storage tanks, vessels, ducts).

Features and Benefits

Crystic VE671 is more reactive than Crystic VE676 because of lower molecular weight. It has a lower styrene content and, also, a lower viscosity than Crystic VE676.

Typical Properties

Property		Liquid Resin
Acid value	mgKOH/g	max. 9
Viscosity Brookfield RVT at 25°C	mPas	450 ± 25*
Colour Gardner		max. 7
Volatile content	%	40 ± 2
Density at 20°C	g/ml	1.04 – 1.06
Shelf life (max 25°C)	months	6
Geltime at 25°C using 100g resin 0.5g – 1.0g DMA (10% in Styrene) 0.7g Cobalt Octoate (3%Co) 2.0g Butanox LPT	minutes	14 – 20*
Time to Peak	minutes	22 – 52
Peak Exotherm	°C	150-170
Property		Cured Cast Resin *
Tensile Strength **	MPa	80
Tensile Modulus **	GPa	3.4
Elongation to Break **	%	4 – 5
Flexural Strength **	MPa	130
Barcol Hardness **	-	40
HDT ***	°C	100 - 105
Water Absorption: 7 days **	mg	40

* Variants available, on request, designed for improved fabrication.

** Curing Schedule: 24 hrs at 20 °C followed by 3 hrs at 80 °C

*** Curing Schedule: 24 hrs at 20 °C followed by 5 hrs at 80°C and then 3 hrs at 120 °C

NB: LPT catalyst should be used in order to reduce the possibility of foam formation. Alternatively, 1–2% of Trigonox 239 with 0.8% Cobalt Octoate (3% Co) can be used. If 1% cobalt is available then an addition of 2.4% will be required.

Laminate Property	Temperature					
	23°C	65 °C	93°C	107°C	121°C	149°C
Temperature (°C)						
Flexural Strength (MPa)	208	196	188	100	38	22
Flexural Modulus (GPa)	7.6	6.9	5.5	3.3	1.6	1.6
Tensile Strength (MPa)	137	139	145	124	76	50
Tensile Modulus (GPa)	9.2	8.9	8.5	6.2	4.3	-
Compressive Strength (MPa)	214	-	-	-	-	-
Glass Content (%)	40					
Laminate Construction:	V/M/M/WR/M/WR/M					

V = veil, M = CSM, WR = woven roving

Post Curing

Satisfactory laminates for many applications can be made from Crystic VE671 by curing at ambient temperature (20°C). For optimum properties and long term performance laminates should be post cured before being put into service. The laminate should be allowed to cure for 24 hours at 20°C and then be oven cured for a minimum of 3 hours at 80°C; the time will be dependent upon the thickness of the laminate. Post curing at 100°C is advisable for high operating temperatures.

Chemical Resistance

Crystic VE671 has excellent chemical resistance to a wide range of substances (acids, alkalis, oxidising agents) at room and elevated temperatures. A separate technical leaflet offers the user a comprehensive guide to the use of Crystic VE671 based laminates in a wide variety of chemical environments.

Storage

Resin should be stored in dark. It is recommended that storage temperature should be less than 20°C, but should not exceed 25°C. In addition, it can be recommended that the vinyl ester resin is weekly aerated with dry and oil free air for 30 minutes through dip pipe (Note: this dip pipe should not contain any zinc or copper alloy). This is done to improve efficiency of inhibitor in order to extend the shelf life of the resin.

Packaging

195 Kg resin is supplied in 210 dm³ protected drums, white coloured outside.

Health & Safety

Please see separate Material Safety Data Sheet.

Version 2 : February 2013

All information on this data sheet is based on laboratory testing and is not intended for design purposes. Scott Bader makes no representations or warranties of any kind concerning this data. Due to variance of storage, handling and application of these materials, Scott Bader cannot accept liability for results obtained. The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.

SCOTT BADER COMPANY LIMITED

Wollaston, Wellingborough, Northamptonshire, NN29 7RL

Telephone: +44 (0) 1933 663100

Facsimile: +44 (0) 1933 666623

www.scottbader.com