Polycin[®] 12

Technical Data Sheet



Product Identification

Polycin[®] 12 is a 100% solids castor oil based reactive diluent having good compatibility and wetting. This polyol is a tetrahydroxy ester, with primary and secondary hydroxyl groups, making it an attractive material for chemical reactions.

| | <u>Property</u> | <u>Value</u> |
|------------|-----------------------------|-------------------|
| Physical | Acid Value | 3 |
| Properties | Appearance | Pale amber liquid |
| | Color, Gardner | 5 |
| | Density, Ibs./gal, 25°C | 8.31 |
| | Equivalent Weight | 170 |
| | Functionality | 4 |
| | Hydroxyl Value | 330 |
| | Moisture, % | 0.03 |
| | Non-Volatile, % | 100 |
| | Specific Gravity, 25°C/25°C | 0.999 |
| | Viscosity, cP @ 25°C | 3,000 |

Applications

- Formulation of 100% solids high performance polyurethane coatings
- Low VOC UV resistant 2-component industrial maintenance coatings and thermosetting OEM coatings
- Property improvements such as; hardness, adhesion, moisture resistance, and chemical resistance in coatings, adhesives, sealants, and elastomeric formulations
- Low VOC force dry and bake topcoats and primers for plastics and metal
- VOC and viscosity reduction in coatings, adhesives and sealants
- Urethane Intermediates, Polymers

For toxicity or regulatory information please consult the Material Safety Data Sheet.

Information contained in this technical data sheet is believed to be accurate. Vertellus Performance Materials Inc. assumes no liability and makes no warranty or representation that the information is correct or complete and EXPRESSLY DISCLAIMS ALL REPRESENTATIONS OR WARRANTIES OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Final determination of suitability of any material and issues of patent infringement is the sole responsibility of the user who alone knows the conditions of intended use. Our customers should ensure that any product incorporating a Vertellus ingredient is safe for its intended use pursuant to applicable law and that any necessary disclosures to consumers have been made.

Vertellus Performance Materials Inc., 2110 High Point Road, Greensboro, NC 27403 USA

USA Tel: 800-227-2436 USA Fax: 336-854-4058 USA Email: VPM-TechServices@vertellus.com

Web: www.vertellus.com